## 🤌 ambient®

## Annapolis White Rigid Core Bamboo \*Opened boxes Flooring



## **Specfications**

| Item No            | 300844149812C  | Warranty               |
|--------------------|--|------------------------|
| Flooring group     | Click Lock BSPC  |                        |
| Price              | 3.7/sq ft  | R value                |
| Species            | Strand Woven Bamboo<br>with rigid SPC core                 | Moisture content       |
| Sq ft/box          | 15.45  | SurfSlip resistanceace |
| Finish             | Accuseal Ultra with<br>aluminum oxide                      |                        |
| Surface            | brushed  | Flammability           |
| Janka rating       | 5342   | Smoke density          |
| Grain              | Bamboo_SPC   |                        |
| Sustainability     | Lacey Act Compliant.                                       | Dimensional            |
| Nailing info       | do not nail  | Stability              |
| Length             | 3 ft (920 mm)  | Coating adhesion       |
| Width              | 5-1/8 in (130 mm)  | Acclimation period     |
| Thickness          | 9/32 in (7mm - includes<br>1mm acoustic pad)               | Weight/box             |
| Wear layer         | 1 mm Strand Bamboo   | Planks/box             |
| Profile            | Click Lock   | Radiant Heat Safe      |
| Profile/edges      | micro bevel  | High traffic           |
| Planks Description | Single length planks: all<br>planks are same<br>dimensions | Pet friendly           |
|                    |  | Install below grade    |
|                    |  | Floating installation  |
|                    |  |                        |

| Warranty               | Lifetime Structural and<br>Finish (residential)                               |
|------------------------|---|
| R value                |   |
| Moisture content       | ASTM D4442, Oven Dry<br>Method: 6%-10% average                                |
| SurfSlip resistanceace | Coefficient of Friction:<br>ASTM D2394 Average;<br>Static 0.586; Sliding 0.59 |
| Flammability           | ASTM E648: Class 1<br>Interior  |
| Smoke density          | ASTM E622: Max 344<br>flaming, 192 non-flaming                                |
| Dimensional            | ASTM D1037 50/90% RH,   |
| Stability              | Linear .03, Thickness<br>1.52, Width .20                                      |
| Coating adhesion       | Classification: 5B  |
| Acclimation period     | 24 hours  |
| Weight/box             | 37  |
| Planks/box             | 12  |
| Radiant Heat Safe      | Yes   |
| High traffic           | Yes   |
| Pet friendly           | Yes   |
| Install below grade    | Yes   |
| Floating installation  | Yes   |
| Installation           | Floating  |