

### **TESTING CONDUCTED ON BEHALF OF THE NAMED CLIENT BELOW:**

Ambient Bamboo Floors 8125 Stayton Dr Unit C Jessup, MD 20794 USA

### **Reporting Laboratory:**

Benchmark International, LLC (BMI)

2710 West 5th Avenue

Eugene, Oregon, USA 97402

Phone: +1 (541) 484-9212 / FAX: +1 (541) 344-2735

#### REPORT INFORMATION:

Report Date: April 27, 2018

**BMI Client/Project Number:** 0721473

Report of: Finished Goods Ind #1 (Face Exposed)

BMI Lab Report Number: 0721473-32

Sample ID Number(s): 2018-0622

rom Wood Products Using a Small Scale Chamber

ASTM D6007-14 Standard Test Method for Determining Formaldehyde Concentration in Air from Wood Products Using a Small Scale Chamber NIOSH 3500: Formaldehyde by VIS (Chromotropic Acid procedure)

Back-to-Back Sample Configuration (Face Exposed)

| CHAMBER TEST CONDITIONS/PARAMETERS                    |                                   |      |      |      |      |      |
|---|-----------------------------------|------|------|------|------|------|
| Product Type:   | Finished Goods                    |      |      |      |      |      |
| Chamber Load Ratio (m <sup>2</sup> /m <sup>3</sup> ): | 0.43                              |      |      |      |      |      |
| Chamber Dimensions (m):                               | 0.49 x 0.49 x 0.49 (Nominal)      |      |      |      |      |      |
| Chamber Volume (m³):                                  | 0.12m <sup>3</sup>                |      |      |      |      |      |
| Air Exchange Rate:                                    | 0.5 +/- 0.05 air changes per hour |      |      |      |      |      |
| Chamber Q/A Ratio (+/- 2%):                           | 1.173                             |      |      |      |      |      |
| No. Specimens in Charge:                              | 1                                 |      |      |      |      |      |
| No. Faces Exposed:                                    | 2                                 |      |      |      |      |      |
| Barometric Pressure (in Hg):                          | 29.6                              |      |      |      |      |      |
| Temperature (°C):                                     | Avg:                              | 25.1 | Min: | 24.9 | Max: | 25.2 |
| Relative Humidity (%):                                | Avg:                              | 50   | Min: | 49   | Max: | 50   |
| Length of Test (minutes):                             | 30                                |      |      |      |      |      |

| TEST RESULTS  |          |  |  |  |  |
|---|----------|--|--|--|--|
|   | Impinger |  |  |  |  |
| Observed Air Flow Rate (Observed L/min):                              | 1.00     |  |  |  |  |
| Corrected Volume of Air Sample (Liters):                              | 30.00    |  |  |  |  |
| Raw Absorbance Values   |          |  |  |  |  |
| Absorbance #1   | 0.002    |  |  |  |  |
| Absorbance #2   | 0.004    |  |  |  |  |
| Absorbance #3   | 0.003    |  |  |  |  |
| Average Absorbance:   | 0.003    |  |  |  |  |
| Unadjusted Concentration (ppm):                                       | 0.01     |  |  |  |  |
| Temperature Correction Factor 25°C:                                   | 0.99     |  |  |  |  |
| Relative Humidity Correction Factor 50% R.H.:                         | 1.01     |  |  |  |  |
| Standardized Concentration (ppm):**                                   | BLQ      |  |  |  |  |
| **BLQ = Test result is below the limit of quantification (<0.015 ppm) |          |  |  |  |  |

This report has been produced for the exclusive use of:

and may not be reproduced except in its entirety, and only with the express written permission of BMI.

All test reports are subject to the current Benchmark Holdings, LLC Inspection and Test Report

Publication Guidelines. Report users are responsible for contacting BMI to obtain a copy of current inspection and test report publication guidelines and/or to obtain written authorization to publish or reproduce this test report.

NOTE 1: Unless otherwise agreed in writing in advance by a duly authorized member of BMI management, test services are subject to the then-current Benchmark Holdings, LLC Standard Terms and Conditions of Service in effect at the time the test sample is submitted to the BMI laboratory. No one other than the named BMI Client above shall be entitled to rely upon this report or the information contained herein. Any such unauthorized reliance on or use of this report will be at the third party's sole risk.

NOTE 2: Services performed for this project have been conducted with a level of care and skill ordinarily exercised by members of the profession currently practicing in this area under similar conditions and constraints. No warranty, expressed or implied, is made.

| PRODUCT AND SAMPLE DATA                    |  |                            |                                       |  |  |
|--|--|----------------------------|---------------------------------------|--|--|
| Product<br>Name/Description:               | 10mm Strand Bamboo HDF Click Lock Flooring |                            |                                       |  |  |
| Panel Manufacturer:                        | Not Specified                              | Production Date:           | 9/12/2017                             |  |  |
| Supplier:<br>(if different than panel mfr) |  | Sample<br>Collection Date: |                                       |  |  |
| Nominal Product<br>Thickness:              |  | Sample Test Date:          | 4/25/2018                             |  |  |
| Nominal Product<br>Dimensions (L x W):     |  |                            | Wrapped Together in<br>Vapor Retarder |  |  |
| Face Surface<br>Condition:                 | Stained/Coated                             | Back Surface<br>Condition: | Stained/Coated                        |  |  |
| Lot/Batch No.:                             | N/S  | Resin Type/Supplier:       | N/S                                   |  |  |

## TEST ANNOTATIONS

- 1) The test chamber is activated under positive pressure. The air sampling rate was 1.0 liters per minute (L/min) for 30 +/- 2 minutes.
- 2) The samples were conditioned for seven (7) days prior to testing. The sample conditioning environment was maintained at 75 +/-  $5^{\circ}F$  (24 +/-  $3^{\circ}C$ ) and 50% +/- 5% relative humidity.
- During conditioning and test, the background concentration of formaldehyde in air was
   0.01 ppm or less.

# OTHER COMMENTS

Not Applicable

Respectfully Submitted,

Laboratory Manager
Benchmark Holdings, LLC (BMH)
Benchmark International, LLC (BMI)



Testing Laboratory